

Return address: P.O. box 337, 7500 AH Enschede, The Netherlands

Vescom B.V.
De heer R. Verlouw
St. Jozefstraat 20
5753 AV DEURNE
The Netherlands

TÜV Rheinland Nederland B.V.
Enschede

Postal address:
P.O. Box 337
7500 AH Enschede
The Netherlands

Parking and delivery:
Josink Esweg 10
7545 PN Enschede
The Netherlands

www.tuv.com/nl

T +31 88 888 7 888
F +31 88 888 7 859

Ronald.boerboom@nl.tuv.com

Report

Received:

Three coated upholstery fabrics further indicated as:

1. Furka 31522 – PO 123889, green. TÜV sample number: MT11-32353.01
2. Furka 31506 – PO 123888, yellow. TÜV sample number: MT11-32353.02
3. Furka 31536 – PO 530223, black. TÜV sample number: MT11-32353.03

Date

18-05-2011

Project number

T11.32353

Phone number client

0031 493 315 833

Fax number client

0031 493 310 677

Your reference

Your shipment 12-05-2011

Article

Coated upholstery fabrics (3x)

Request:

To determine the abrasion resistance Martindale and the tensile strength.

Appendix

-

Test method:

Abrasion resistance : ISO 12947-2:1998/C1:2002. Pressure on specimen:
12 kPa. End point as agreed with client: hole in coating.
Tensile strength : ISO 1421:1998. Strip method. Gauge length in length
direction 200 mm in width direction 100 mm, rate of
extension 100 mm/min, pretension 10 N, test in fivefold,
tested in conditioned state.

Test conditions:

Temperature : 20 ± 2 °C
Relative humidity : 65 ± 4%
Date of testing : 13/16/17-05-2011

TRN applies General Terms & Conditions which
are filed at the office of the Clerk for civil affairs
at the Court in Zutphen (the Netherlands) under
number 35/2010, dated November 17th 2010.

Date
18-05-2011

Project number
T11.32353

Test results:

➤ *Abrasion resistance*

TÜV sample number	Number of cycles, 12 kPa				
	1	2	3	4	Average
MT11-32353.01 Furka 31522, green.	>125.000	>125.000	>125.000	>125.000	>125.000
MT11-32353.02 Furka 31506, yellow.	>125.000	>125.000	>125.000	>125.000	>125.000
MT11-32353.03 Furka 530223, black.	>125.000	>125.000	>125.000	>125.000	>125.000

Page
2/3

➤ *Tensile strength*

MT11-32353.01 Furka 31522, green.	Length direction		Width direction	
	F _{max} (N)	elongation (%)	F _{max} (N)	elongation (%)
Sample 1	652	30.0	310	248
Sample 2	658	30.0	292	241
Sample 3	665	31.0	314	250
Sample 4	629	29.0	295	241
Sample 5	623	30.0	282	233
Mean	645	30.0	299	243

➤ *Tensile strength*

MT11-32353.02 Furka 31506, yellow.	Length direction		Width direction	
	F _{max} (N)	elongation (%)	F _{max} (N)	elongation (%)
Sample 1	425	40.0	301	176
Sample 2	402	37.0	308	191
Sample 3	405	37.0	305	181
Sample 4	402	36.0	289	167
Sample 5	376	34.0	294	182
Mean	402	37.0	299	179

Date
18-05-2011

Project number
T11.32353

Page
3/3

➤ *Tensile strength*

MT11-32353.03 Furka 530223, black.	longitudinal direction		transverse direction	
	F _{max} (N)	elongation (%)	F _{max} (N)	elongation (%)
Sample 1	377	35.0	276	121
Sample 2	394	35.0	282	129
Sample 3	364	34.0	276	127
Sample 4	382	34.0	268	127
Sample 5	381	34.0	282	123
Mean	379	34.0	277	125

Remark: Force at break see appendix.

Project leader:
R. Boerboom, BSc.

Visa:
H. Weustink, MSc.

All rights reserved.

*No part of this report may be reproduced, provided to and/or examined by third parties, and/or published by print, photoprint, microfilm, in electronic form or any other means without the explicit previous written consent of TÜV Rheinland Nederland B.V.. The results are based upon the samples received and have not to be representative for the total production. Besides TÜV Rheinland Nederland B.V. had no influence on the sampling.
In case this report was drafted within the context of an assignment to TÜV Rheinland Nederland B.V., the rights and obligations of contracting parties are subject to the General Terms & Conditions for Advisory, Research and Certification assignments to TÜV Rheinland Nederland B.V. and/or the relevant agreement concluded between the contracting parties.*

© 2010 TÜV Rheinland Nederland B.V.