

## CERTIFICATE OF TESTING

For the Account Of: Raxon Fabrics  
2289 Ross Mill Road  
Henderson, NC 27536  
Contact: Barbara Crane

Client's Identification: Lamu Test #459  
(Vescom B.V.; Sint Jozestraat 20; 5753 Av Duerne)

**TEST PERFORMED** Abrasion Resistance of Textile Fabrics (Oscillatory Cylinder Method) ASTM D4157-13

### TEST RESULTS

Number of Double Rubs	Warp (Length) Specimens	Fill (Width) Specimens
30,000	Breakage in 1 <sup>st</sup> specimen	No breakage/wear
35,000	Breakage in 2 <sup>nd</sup> specimen	No breakage/wear

### INTERPRETATION USED

- Option 1 The end point is reached on a woven fabric when two or more yarns have broken or on a knitted fabric, when a hole appears.
- Option 2 The end point is reached when there is a change in shade or appearance that is sufficient to cause a customer to complain.

### NOTES

**Abradant Used:**  ACT Standard #10 Cotton Duck  Wire Screen  
**Samples Backed with Masking Tape:**  Yes  No  
**Tension:** 4 pounds  
**Compression:** 3 pounds

### ACCEPTANCE CRITERIA


A.C.T. Standard	Acceptance Criteria
General Contract Upholstery	No appreciable breakage or wear after 15,000 double rubs
Heavy Duty Upholstery	No appreciable breakage or wear after 30,000 double rubs

### CONCLUSION

Based on the above Results and the A.C.T. Standard, the item tested:

Unrated  
 General Contract Upholstery  
 Heavy Duty Upholstery

**CERTIFICATION** I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

  
Authorized Signature CR