

Vescom bv
Dhr. Twan Ramaekers
P.O. Box 70
5750 AB DEURNE
Nederland



Your notice of
 20-11-2017

Your reference
 SO-1167023

Date
 15-12-2017

Analysis Report 17.06676.01

Required tests :

IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 8	Fire tests - Test for upholstered furniture - smouldering cigarette test
IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 8	Fire tests - Test for upholstered furniture - Match flame equivalent

Identification number	Information given by the client	Date of receipt
T1725450	PONZA	20-11-2017

Petra Wittevrongel

Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
 The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
 In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

CENTEXBEL • textile competence centre • www.centexbel.be • www.vkc.be

Inrichting erkend bij toepassing van de besluitwet van 30-01-1947 • Établissement reconnu par application de l'arrêté-loi du 30-01-1947
 GENT • Technologiepark 7 • BE-9052 Zwijnaarde, Belgium • phone +32 9 220 41 51 • fax +32 9 220 49 55 • gent@centexbel.be
 GRÂCE-HOLLOGNE • Rue du Travail 5 • BE-4460 Grâce-Hollogne, Belgium • phone +32 4 296 82 00 • g-h@centexbel.be
 KORTRIJK • Etienne Sabbelaan 49 • BE-8500 Kortrijk, Belgium • phone +32 56 281828 • fax +32 56 281830 • info@vkc.be
 VAT BE 0459.218.289 • IBAN BE44 2100 4729 6545 • BIC GEBABEBB

Reference: T1725450 - PONZA

IMO upholstered furniture

Information given by the client

Type of furniture

Upholstery

Fabric

Composition

100% polyester (Trevira CS)

Structure

Vervet weave

Number of threads - warp

Warp: 25/cm, pile: 12/cm

Number of threads - weft

15/cm

Yarn count - warp

Warp: Nm 40/2, pile: Nm30/1

Yarn count - weft

Nm 20/1

Thickness in mm

7

Weight per unit area

605 g/m²

Colour

702726

Inherently FR treated

yes

Reference: T1725450 - PONZA

Fire tests - Test for upholstered furniture - smouldering cigarette test

Date of ending the test	12-12-2017
Standard used	IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 8
Deviation from the standard	-
Conditioning	23°C, relative humidity 50%

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Filling SB 36140 (Recticel) - fire retardant foam - $\pm 36 \text{ kg/m}^3$

Ignition source: smouldering cigarette with the following specifications

Length: $(70 \pm 4) \text{ mm}$

Diameter: $(8.0 \pm 0.5) \text{ mm}$

Mass: $(0.95 \pm 0.15) \text{ mm}$

Smouldering rate: $(11.0 \pm 4.0) \text{ min} / 50 \text{ mm}$

	1	2
Smouldering criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoulders to extremities	no	no
Smoulders through thickness	no	no
Smoulders more than 1 hour	no	no
Final examination / active smouldering	no	no
Flaming criteria		
Occurrence of flames	no	no
	non-ignition	non-ignition

Conclusion Pass

Reference: T1725450 - PONZA

Fire tests - Test for upholstered furniture - Match flame equivalent

Date of ending the test 12-12-2017
 Standard used IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 8

Deviation from the standard -

Conditioning 23°C, relative humidity 50%

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Filling SB 36140 (Recticel) - fire retardant foam - ± 36 kg/m³

Flame application time (s) 20

	1	2
Smouldering criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoke/heat/glowing more than 120 s	no	no
Final examination / active smouldering	no	no
Flaming criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Flaming > 120 s	no	no
Afterflame time (s)	0	0
	non-ignition	non-ignition

Conclusion Pass