



TESTING CERT. #3193.01

Report Number: 18-001192

Revision Number:1

Date Order Received: 02/27/2018

For the Account of: Vescom America Inc. 2289 Ross Mill Road Henderson, NC 272537

Client's Identification: Burano 8003 Test #581

CERTIFICATE OF TESTING

TEST PERFORMED: Resistance to Slippage of Yarns in Woven Fabrics Using a Standard Seam ASTM D434-95 as Modified by ASTM D3597-02(2013)

TEST RESULTS

Table with 3 columns: Specimen, Warp Yarn Slippage (lbf), Type of Failure. Rows 1-5 and Avg. Warp.

Table with 3 columns: Specimen, Fill Yarn Slippage (lbf), Type of Failure. Rows 1-5 and Avg. Fill.

ABBREVIATIONS USED

- SB Seam broke before 1/4" slippage - Results should reflect this
SS 1/4" slippage occurred - Note: Actual slippage of yarns is visible
FB Fabric broke before 1/4" slippage - Note: Actual breakage is visible

NOTES

Equipment Used: Tinius Olson H5KT Universal Testing Machine
Seam Description: Per ASTM D3597-02
Seam Type: Standard Lockstitch
Stitches per Inch: 7 -8 stitches per inch
Needle Used: Chrome plated 0.063 inch diameter
Thread: No. 24-4 hard finish Z-twist cotton thread

ACCEPTANCE CRITERIA

A.C.T. Standard: Drapery fabrics over 6oz/sq. yard
Acceptance Criteria: 25 lbs. Minimum

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Berta Stiver (handwritten signature)

Authorized Signature

Date Order Completed: 03/14/2018