

CERTIFICATE OF TESTING

For the Account Of: Raxon Fabrics
2289 Ross Mill Road
Henderson, NC 27536

Contact: Barbara Crane

Client's Identification: Lani Test #460
(Vescom B.V.; Sint Jozestraat 20; 5753 Av Duerne)

TEST PERFORMED Breaking Strength and Elongation of Textile Fabrics (Grab Test) ASTM D5034-09(2013)(G-E)

TEST RESULTS

Specimen	Breaking Force (lbf)	
1	211	
2	211	
3	205	
4	203	
5	201	
		Avg of Warp: 206
6	201	
7	203	
8	209	
9	209	
10	198	
11	198	
12	198	
13	203	
		Avg of Fill: 202


NOTES

Equipment Used: Tinius Olson H5KT Universal Testing Machine
Load Cell Maximum: 1000 pounds
Jaw Size: 1 inch x 1 inch (face and back), rubber coated
Test Conditions: 70 ±4°F, 65 ±5% Relative Humidity
Sampling Method: As Received

ACCEPTANCE CRITERIA

A.C.T. Standard	Acceptance Criteria
Upholstery	50 pounds minimum
Panels and Upholstered Walls	35 pounds minimum

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.



 Authorized Signature CR