



TESTING CERT. #3193.01

Report Number: 18-001185
Revision Number:1
Date Order Received: 02/27/2018

For the Account of: Vescom America Inc.
2289 Ross Mill Road
Henderson, NC 272537

Client's Identification: Nauru 7003 Test #593

CERTIFICATE OF TESTING

TEST PERFORMED: Pilling Resistance and Other Related Surface Changes of Textile Fabrics : Brush Pilling Tester ASTM D3511/D3511M-16

TEST RESULTS

	Rating
Left	4.5
Center	4.5
Right	4.5
Average Rating	4.5

RATING SYSTEM

- Class 5.0 No Pilling
- Class 4.0 Slight Pilling
- Class 3.0 Moderate Pilling
- Class 2.0 Severe Pilling
- Class 1.0 Very Severe Pilling

NOTES

- Test Conditions:** 70 ±4°F, 65 ±5% Relative Humidity
- Sampling Method:** As Received
- Viewing Apparatus:** Macbeth Lightbooth
- Viewing Option:** 45 degree
- Rating Standard:** ADJD3512 Photographic Standards
- Running Times:** 4 minutes brushing / 2 minutes pilling

ACCEPTANCE CRITERIA

- A.C.T. Standard:** Acceptance Criteria
- Upholstery Class 3 minimum

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature

Date Order Completed: 03/01/2018