



TESTING CERT. #3193.01

Report Number: 18-001199  
Revision Number:1  
Date Order Received: 02/27/2018

For the Account of: Vescom America Inc.  
2289 Ross Mill Road  
Henderson, NC 272537

Client's Identification: Cres 7010 Test #596

### CERTIFICATE OF TESTING

**TEST PERFORMED:** Pilling Resistance and Other Related Surface Changes of Textile Fabrics : Brush Pilling Tester ASTM D3511/D3511M-16

#### TEST RESULTS

	Rating
Left	5.0
Center	5.0
Right	5.0
Average Rating	5.0

#### RATING SYSTEM

- Class 5.0 No Pilling
- Class 4.0 Slight Pilling
- Class 3.0 Moderate Pilling
- Class 2.0 Severe Pilling
- Class 1.0 Very Severe Pilling

#### NOTES

- Test Conditions:** 70 ±4°F, 65 ±5% Relative Humidity
- Sampling Method:** As Received
- Viewing Apparatus:** Macbeth Lightbooth
- Viewing Option:** 45 degree
- Rating Standard:** ADJD3512 Photographic Standards
- Running Times:** 4 minutes brushing / 2 minutes pilling

#### ACCEPTANCE CRITERIA

- A.C.T. Standard:** Acceptance Criteria
- Upholstery Class 3 minimum

**CERTIFICATION** I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature

Date Order Completed: 03/01/2018