



TESTING CERT. #3193.01

Report Number: 18-001199

Revision Number:1

Date Order Received: 02/27/2018

For the Account of: Vescom America Inc.
2289 Ross Mill Road
Henderson, NC 272537

Client's Identification: Cres 7010 Test #596

CERTIFICATE OF TESTING

TEST PERFORMED: Resistance to Slippage of Yarns in Woven Fabrics Using a Standard Seam ASTM D4034-92

TEST RESULTS

Table with 6 columns: Specimen, Warp Yarn Slippage (lbf), Type of Failure, Specimen, Fill Yarn Slippage (lbf), Type of Failure. Contains data for 5 specimens and average values for Warp and Fill.

ABBREVIATIONS USED

- SB Seam broke before 1/4" slippage - Results should reflect this
SS 1/4" slippage occurred - Note: Actual slippage of yarns is visible
FB Fabric broke before 1/4" slippage - Note: Actual breakage is visible

NOTES

Equipment Used: Tinius Olson H5KT Universal Testing Machine
Seam Description:

Seam Type Standard Lockstitch
Stitches per Inch 7 ± 0.5 stitches per inch
Needle Used Size 22 NM: 140, 135x17 ball point needle
Thread Nymo EX Bonded Nylon thread; 5x is used for the bobbin and 8x is used for the needle

ACCEPTANCE CRITERIA

A.C.T. Standard Upholstery
Acceptance Criteria 25 lbs. Minimum

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Berta Stiver (Handwritten signature)

Authorized Signature

Date Order Completed: 03/06/2018