

Lightfastness Tapetex Wall Materials - 67 - Nonwoven

E.031711D.v1

Testing as per ISO 105-B02:2014

Testresults are based upon 216 hours of exposure. The test was stopped at 216 hours.

Location test : Tapetex BV, Helmond, The Netherlands

Testing machinery : Heraeus original Hanau Xenotest 150S

Standard blue scale 0 - 8

Humidity 65%, Blackpanel temperature 45° Celsius

<u>Pattern</u>	<u>Testresult</u>	<u>Quality Number</u>
Maestro	6	67-1650 / 67-1659
Tuscany	6	67-1660 / 67-1669
Montresor	6	67-1670 / 67-1674
Kai	6	67-1680 / 67-1684
Bora	6	67-1690 / 67-1699
Deauville	6	67-1700 / 67-1709
Orienta	6	67-1710 / 67-1719
Montado	6	67-1720 / 67-1729
Venetian	6	67-1730 / 67-1734
Terral	6	67-1740 / 67-1749
Samsara	6	67-1750 / 67-1754
Rondo	6	67-1760 / 67-1764
Grandessa	6	67-1770 / 67-1779
Chambord	6	67-1780 / 67-1789
Tiffany	6	67-1790 / 67-1794
Fenda	6	67-1800 / 67-1809
Corona	6	67-1810 / 67-1819
Primavera	6	67-1820 / 67-1824

---

<u>Pattern</u>	<u>Testresult</u>	<u>Quality Number</u>
Mirabel	6	67-1830 / 67-1839
Tartano	6	67-1840 / 67-1844
Lino	6	67-1850 / 67-1859
Zagara	6	67-1860 / 67-1869
Sashiko	6	67-1870 / 67-1874
Canvasa	6	67-1880 / 67-1889