

Vescom Textiles bv
Dhr. Twan Ramaekers
Postbus 349
5750 AH DEURNE
Nederland



Your notice of
19-04-2018

Your reference

Date
08-05-2018

Analysis Report 18.02345.01

Required tests :

ISO 105-E16 (2006)

ISO 105-E04 (2013)

ISO 105-D01 (2010)

ISO 105-C06 (2010)

Determination of the colour fastness to spotting: water

Determination of the colour fastness to perspiration

Determination of the colour fastness to dry cleaning

Determination of the colour fastness to domestic and commercial laundering

Identification number	Information given by the client	Date of receipt
T1809532	Zanzibar 7008	19-04-2018
T1809533	Togo 7031	19-04-2018
T1809534	Ariana 7029	19-04-2018
T1809535	Ponza 7027	19-04-2018

Eddy Albrecht

Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
 The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
 In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

CENTEXBEL • textile competence centre • www.centexbel.be • www.vkc.be

Inrichting erkend bij toepassing van de besluitwet van 30-01-1947 • Établissement reconnu par application de l'arrêté-loi du 30-01-1947
 GENT • Technologiepark 7 • BE-9052 Zwijnaarde, Belgium • phone +32 9 220 41 51 • fax +32 9 220 49 55 • gent@centexbel.be
 GRÂCE-HOLLOGNE • Rue du Travail 5 • BE-4460 Grâce-Hollogne, Belgium • phone +32 4 296 82 00 • g-h@centexbel.be
 KORTRIJK • Etienne Sabbelaan 49 • BE-8500 Kortrijk, Belgium • phone +32 56 281828 • fax +32 56 281830 • info@vkc.be
 VAT BE 0459.218.289 • IBAN BE44 2100 4729 6545 • BIC GEBABEBB

Reference: T1809532 - Zanzibar 7008

Determination of the colour fastness to spotting: water

Date of ending the test 07-05-2018
Standard used ISO 105-E16 (2006)

Deviation from the standard -

Results
Evaluation using grey scales

	Numerical rating
Change in colour of the specimen, inside the spot	5
Change in colour of the specimen, at the edge of the spot	5

Grading against grey scale for change in colour and/or staining:

Use of a 9 point scale from 5 to 1; where 5 is excellent and 1 is poor. Intermediate values like 2-3 are possible.

Reference: T1809532 - Zanzibar 7008

Determination of the colour fastness to perspiration

Date of ending the test 07-05-2018
Standard used ISO 105-E04 (2013)

Deviation from the standard
Apparatus Perspirometer

Results

Alkaline solution

Numerical rating	
Change in colour	4-5
Staining on cotton	4
Staining on wool	4

Acid solution

Numerical rating	
Change in colour	4-5
Staining on cotton	4
Staining on wool	4-5

Grading against grey scale for change in colour and/or staining:

Use of a 9 point scale from 5 to 1; where 5 is excellent and 1 is poor. Intermediate values like 2-3 are possible.

Reference: T1809532 - Zanzibar 7008

Determination of the colour fastness to dry cleaning

Date of ending the test 07-05-2018
Standard used ISO 105-D01 (2010)

Apparatus Gyrowash
Solvent Tetrachloroethylene

Results

Monofibre

Numerical rating	
Change in colour	5
Staining on cotton	5
Staining on wool	5

Grading against grey scale for change in colour and/or staining:

Use of a 9 point scale from 5 to 1; where 5 is excellent and 1 is poor. Intermediate values like 2-3 are possible.

Reference: T1809532 - Zanzibar 7008

Determination of the colour fastness to domestic and commercial laundering

Date of ending the test 07-05-2018
Standard used ISO 105-C06 (2010)

Deviation from the standard 30°C instead of 40°C
Apparatus Gyrowash
Detergent ECE reference detergent
Wash procedure Method A2S
Temperature 30°C
Use of steel balls Yes, number :10
Treatment in acetic acid reagent No

Results

Monofibre

Numerical rating	
Change in colour	4-5
Staining on cotton	4
Staining on wool	3-4

Grading against grey scale for change in colour and/or staining:

Use of a 9 point scale from 5 to 1; where 5 is excellent and 1 is poor. Intermediate values like 2-3 are possible.

Reference: T1809532 - Zanzibar 7008

Determination of the colour fastness to domestic and commercial laundering

Date of ending the test 07-05-2018
Standard used ISO 105-C06 (2010)

Apparatus Gyrowash
Detergent ECE reference detergent
Wash procedure Method C2S
Temperature 60°C
Use of steel balls Yes, number :10
Treatment in acetic acid reagent No

Results

Monofibre

Numerical rating	
Change in colour	4
Staining on cotton	3
Staining on viscose	3

Grading against grey scale for change in colour and/or staining:

Use of a 9 point scale from 5 to 1; where 5 is excellent and 1 is poor. Intermediate values like 2-3 are possible.

Reference: T1809532 - Zanzibar 7008

Determination of the colour fastness to domestic and commercial laundering

Date of ending the test 07-05-2018
Standard used ISO 105-C06 (2010)

Apparatus Gyrowash
Detergent ECE reference detergent
Wash procedure Method B2S
Temperature 50°C
Use of steel balls Yes, number :10
Treatment in acetic acid reagent No

Results

Monofibre

Numerical rating	
Change in colour	4
Staining on cotton	3-4
Staining on viscose	3-4

Grading against grey scale for change in colour and/or staining:

Use of a 9 point scale from 5 to 1; where 5 is excellent and 1 is poor. Intermediate values like 2-3 are possible.

Reference: T1809532 - Zanzibar 7008

Determination of the colour fastness to domestic and commercial laundering

Date of ending the test 07-05-2018
Standard used ISO 105-C06 (2010)

Apparatus Gyrowash
Detergent ECE reference detergent
Wash procedure Method D2S
Temperature 70°C
Use of steel balls Yes, number :10
Treatment in acetic acid reagent No

Results

Monofibre

Numerical rating	
Change in colour	3-4
Staining on cotton	2-3
Staining on viscose	3

Grading against grey scale for change in colour and/or staining:

Use of a 9 point scale from 5 to 1; where 5 is excellent and 1 is poor. Intermediate values like 2-3 are possible.

Reference: T1809533 - Togo 7031

Determination of the colour fastness to spotting: water

Date of ending the test 07-05-2018
Standard used ISO 105-E16 (2006)

Deviation from the standard -

Results
Evaluation using grey scales

	Numerical rating
Change in colour of the specimen, inside the spot	4-5
Change in colour of the specimen, at the edge of the spot	4-5

Grading against grey scale for change in colour and/or staining:

Use of a 9 point scale from 5 to 1; where 5 is excellent and 1 is poor. Intermediate values like 2-3 are possible.

Reference: T1809533 - Togo 7031

Determination of the colour fastness to perspiration

Date of ending the test 07-05-2018
Standard used ISO 105-E04 (2013)

Deviation from the standard
Apparatus Perspirometer

Results

Alkaline solution

Numerical rating	
Change in colour	4-5
Staining on cotton	2-3
Staining on wool	3

Acid solution

Numerical rating	
Change in colour	4-5
Staining on cotton	3
Staining on wool	3-4

Grading against grey scale for change in colour and/or staining:

Use of a 9 point scale from 5 to 1; where 5 is excellent and 1 is poor. Intermediate values like 2-3 are possible.

Reference: T1809533 - Togo 7031

Determination of the colour fastness to dry cleaning

Date of ending the test 07-05-2018
Standard used ISO 105-D01 (2010)

Apparatus Gyrowash
Solvent Tetrachloroethylene

Results

Monofibre

Numerical rating	
Change in colour	4-5
Staining on cotton	4-5
Staining on wool	4-5

Grading against grey scale for change in colour and/or staining:

Use of a 9 point scale from 5 to 1; where 5 is excellent and 1 is poor. Intermediate values like 2-3 are possible.

Reference: T1809533 - Togo 7031

Determination of the colour fastness to domestic and commercial laundering

Date of ending the test 08-05-2018
Standard used ISO 105-C06 (2010)

Deviation from the standard 30°C instead of 40°C
Apparatus Gyrowash
Detergent ECE reference detergent
Wash procedure Method A2S
Temperature 30°C
Use of steel balls Yes, number :10
Treatment in acetic acid reagent No

Results

Monofibre

Numerical rating	
Change in colour	4-5
Staining on cotton	3
Staining on wool	3

Grading against grey scale for change in colour and/or staining:

Use of a 9 point scale from 5 to 1; where 5 is excellent and 1 is poor. Intermediate values like 2-3 are possible.

Reference: T1809533 - Togo 7031

Determination of the colour fastness to domestic and commercial laundering

Date of ending the test 08-05-2018
Standard used ISO 105-C06 (2010)

Apparatus Gyrowash
Detergent ECE reference detergent
Wash procedure Method B2S
Temperature 50°C
Use of steel balls Yes, number :10
Treatment in acetic acid reagent No

Results

Monofibre

Numerical rating	
Change in colour	4
Staining on cotton	2-3
Staining on viscose	2-3

Grading against grey scale for change in colour and/or staining:

Use of a 9 point scale from 5 to 1; where 5 is excellent and 1 is poor. Intermediate values like 2-3 are possible.

Reference: T1809533 - Togo 7031

Determination of the colour fastness to domestic and commercial laundering

Date of ending the test 08-05-2018
Standard used ISO 105-C06 (2010)

Apparatus Gyrowash
Detergent ECE reference detergent
Wash procedure Method C2S
Temperature 60°C
Use of steel balls Yes, number :10
Treatment in acetic acid reagent No

Results

Monofibre

Numerical rating	
Change in colour	3-4
Staining on cotton	2
Staining on viscose	2

Grading against grey scale for change in colour and/or staining:

Use of a 9 point scale from 5 to 1; where 5 is excellent and 1 is poor. Intermediate values like 2-3 are possible.

Reference: T1809533 - Togo 7031

Determination of the colour fastness to domestic and commercial laundering

Date of ending the test 08-05-2018
Standard used ISO 105-C06 (2010)

Apparatus Gyrowash
Detergent ECE reference detergent
Wash procedure Method D2S
Temperature 70°C
Use of steel balls Yes, number :10
Treatment in acetic acid reagent No

Results

Monofibre

Numerical rating	
Change in colour	3
Staining on cotton	1-2
Staining on viscose	1-2

Grading against grey scale for change in colour and/or staining:

Use of a 9 point scale from 5 to 1; where 5 is excellent and 1 is poor. Intermediate values like 2-3 are possible.

Reference: T1809534 - Ariana 7029

Determination of the colour fastness to spotting: water

Date of ending the test 07-05-2018
Standard used ISO 105-E16 (2006)

Deviation from the standard -

Results
Evaluation using grey scales

	Numerical rating
Change in colour of the specimen, inside the spot	3-4
Change in colour of the specimen, at the edge of the spot	3-4

Grading against grey scale for change in colour and/or staining:

Use of a 9 point scale from 5 to 1; where 5 is excellent and 1 is poor. Intermediate values like 2-3 are possible.

Reference: T1809534 - Ariana 7029

Determination of the colour fastness to perspiration

Date of ending the test 08-05-2018
Standard used ISO 105-E04 (2013)

Deviation from the standard
Apparatus Perspirometer

Results

Alkaline solution

Numerical rating	
Change in colour	4-5
Staining on cotton	4-5
Staining on wool	4-5

Acid solution

Numerical rating	
Change in colour	4-5
Staining on cotton	4-5
Staining on wool	4-5

Grading against grey scale for change in colour and/or staining:

Use of a 9 point scale from 5 to 1; where 5 is excellent and 1 is poor. Intermediate values like 2-3 are possible.

Reference: T1809534 - Ariana 7029

Determination of the colour fastness to dry cleaning

Date of ending the test 07-05-2018
Standard used ISO 105-D01 (2010)

Apparatus Gyrowash
Solvent Tetrachloroethylene

Results

Monofibre

Numerical rating	
Change in colour	5
Staining on cotton	4-5
Staining on wool	5

Grading against grey scale for change in colour and/or staining:

Use of a 9 point scale from 5 to 1; where 5 is excellent and 1 is poor. Intermediate values like 2-3 are possible.

Reference: T1809534 - Ariana 7029

Determination of the colour fastness to domestic and commercial laundering

Date of ending the test 08-05-2018
Standard used ISO 105-C06 (2010)

Deviation from the standard 30°C instead of 40°C
Apparatus Gyrowash
Detergent ECE reference detergent
Wash procedure Method A2S
Temperature 30°C
Use of steel balls Yes, number :10
Treatment in acetic acid reagent No

Results

Monofibre

Numerical rating	
Change in colour	4-5
Staining on cotton	3-4
Staining on wool	4

Grading against grey scale for change in colour and/or staining:

Use of a 9 point scale from 5 to 1; where 5 is excellent and 1 is poor. Intermediate values like 2-3 are possible.

Reference: T1809534 - Ariana 7029

Determination of the colour fastness to domestic and commercial laundering

Date of ending the test 08-05-2018
Standard used ISO 105-C06 (2010)

Apparatus Gyrowash
Detergent ECE reference detergent
Wash procedure Method B2S
Temperature 50°C
Use of steel balls Yes, number :10
Treatment in acetic acid reagent No

Results

Monofibre

Numerical rating	
Change in colour	4-5
Staining on cotton	3-4
Staining on viscose	3-4

Grading against grey scale for change in colour and/or staining:

Use of a 9 point scale from 5 to 1; where 5 is excellent and 1 is poor. Intermediate values like 2-3 are possible.

Reference: T1809534 - Ariana 7029

Determination of the colour fastness to domestic and commercial laundering

Date of ending the test 08-05-2018
Standard used ISO 105-C06 (2010)

Apparatus Gyrowash
Detergent ECE reference detergent
Wash procedure Method C2S
Temperature 60°C
Use of steel balls Yes, number :10
Treatment in acetic acid reagent No

Results

Monofibre

Numerical rating	
Change in colour	4-5
Staining on cotton	3
Staining on viscose	3

Grading against grey scale for change in colour and/or staining:

Use of a 9 point scale from 5 to 1; where 5 is excellent and 1 is poor. Intermediate values like 2-3 are possible.

Reference: T1809534 - Ariana 7029

Determination of the colour fastness to domestic and commercial laundering

Date of ending the test 08-05-2018
Standard used ISO 105-C06 (2010)

Apparatus Gyrowash
Detergent ECE reference detergent
Wash procedure Method D2S
Temperature 70°C
Use of steel balls Yes, number :10
Treatment in acetic acid reagent No

Results

Monofibre

Numerical rating	
Change in colour	4-5
Staining on cotton	2-3
Staining on viscose	2-3

Grading against grey scale for change in colour and/or staining:

Use of a 9 point scale from 5 to 1; where 5 is excellent and 1 is poor. Intermediate values like 2-3 are possible.

Reference: T1809535 - Ponza 7027

Determination of the colour fastness to spotting: water

Date of ending the test 07-05-2018
Standard used ISO 105-E16 (2006)

Deviation from the standard -

Results
Evaluation using grey scales

	Numerical rating
Change in colour of the specimen, inside the spot	5
Change in colour of the specimen, at the edge of the spot	5

Grading against grey scale for change in colour and/or staining:

Use of a 9 point scale from 5 to 1; where 5 is excellent and 1 is poor. Intermediate values like 2-3 are possible.

Reference: T1809535 - Ponza 7027

Determination of the colour fastness to perspiration

Date of ending the test 08-05-2018
Standard used ISO 105-E04 (2013)

Deviation from the standard
Apparatus Perspirometer

Results

Alkaline solution

Numerical rating	
Change in colour	4-5
Staining on polyester	5
Staining on cotton	5

Acid solution

Numerical rating	
Change in colour	4-5
Staining on polyester	5
Staining on cotton	5

Grading against grey scale for change in colour and/or staining:

Use of a 9 point scale from 5 to 1; where 5 is excellent and 1 is poor. Intermediate values like 2-3 are possible.

Reference: T1809535 - Ponza 7027

Determination of the colour fastness to dry cleaning

Date of ending the test 07-05-2018
Standard used ISO 105-D01 (2010)

Apparatus Gyrowash
Solvent Tetrachloroethylene

Results

Monofibre

Numerical rating	
Change in colour	4-5
Staining on polyester	4-5
Staining on cotton	5

Grading against grey scale for change in colour and/or staining:

Use of a 9 point scale from 5 to 1; where 5 is excellent and 1 is poor. Intermediate values like 2-3 are possible.

Reference: T1809535 - Ponza 7027

Determination of the colour fastness to domestic and commercial laundering

Date of ending the test 08-05-2018
Standard used ISO 105-C06 (2010)

Deviation from the standard 30°C instead of 40°C
Apparatus Gyrowash
Detergent ECE reference detergent
Wash procedure Method A2S
Temperature 30°C
Use of steel balls Yes, number :10
Treatment in acetic acid reagent No

Results

Monofibre

Numerical rating	
Change in colour	5
Staining on polyester	5
Staining on cotton	5

Grading against grey scale for change in colour and/or staining:

Use of a 9 point scale from 5 to 1; where 5 is excellent and 1 is poor. Intermediate values like 2-3 are possible.

Reference: T1809535 - Ponza 7027

Determination of the colour fastness to domestic and commercial laundering

Date of ending the test 08-05-2018
Standard used ISO 105-C06 (2010)

Apparatus Gyrowash
Detergent ECE reference detergent
Wash procedure Method B2S
Temperature 50°C
Use of steel balls Yes, number :10
Treatment in acetic acid reagent No

Results

Monofibre

Numerical rating	
Change in colour	4-5
Staining on polyester	5
Staining on cotton	5

Grading against grey scale for change in colour and/or staining:

Use of a 9 point scale from 5 to 1; where 5 is excellent and 1 is poor. Intermediate values like 2-3 are possible.

Reference: T1809535 - Ponza 7027

Determination of the colour fastness to domestic and commercial laundering

Date of ending the test 08-05-2018
Standard used ISO 105-C06 (2010)

Apparatus Gyrowash
Detergent ECE reference detergent
Wash procedure Method C2S
Temperature 60°C
Use of steel balls Yes, number :10
Treatment in acetic acid reagent No

Results

Monofibre

Numerical rating	
Change in colour	4-5
Staining on polyester	5
Staining on cotton	5

Grading against grey scale for change in colour and/or staining:

Use of a 9 point scale from 5 to 1; where 5 is excellent and 1 is poor. Intermediate values like 2-3 are possible.

Reference: T1809535 - Ponza 7027

Determination of the colour fastness to domestic and commercial laundering

Date of ending the test 08-05-2018
Standard used ISO 105-C06 (2010)

Apparatus Gyrowash
Detergent ECE reference detergent
Wash procedure Method D2S
Temperature 70°C
Use of steel balls Yes, number :10
Treatment in acetic acid reagent No

Results

Monofibre

Numerical rating	
Change in colour	4-5
Staining on polyester	5
Staining on cotton	5

Grading against grey scale for change in colour and/or staining:

Use of a 9 point scale from 5 to 1; where 5 is excellent and 1 is poor. Intermediate values like 2-3 are possible.