

Vescom BV
Sint-jozefstraat 20
5753 AV Deurne
Nederland



Your notice of
07-03-2018

Your reference

Date
11-04-2018

Analysis Report 18.01439.04

Required tests :
BS 5852 (2006)

Clause 11 (upholstery composite) - Assessment of the
ignitability of upholstered seating - crib ignition source no.
5

| Identification number | Information given by the client | Date of receipt |
|-----------------------|---|-----------------|
| T1805567 | Noss 7058 100% PES (Trevira CS), 655 g/m ² | 07-03-2018 |

Gina Créelle

Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

CENTEXBEL • textile competence centre • www.centexbel.be • www.vkc.be

Inrichting erkend bij toepassing van de besluitwet van 30-01-1947 • Établissement reconnu par application de l'arrêté-loi du 30-01-1947
GENT • Technologiepark 7 • BE-9052 Zwijnaarde, Belgium • phone +32 9 220 41 51 • fax +32 9 220 49 55 • gent@centexbel.be
GRACE-HOLLOGNE • Rue du Travail 5 • BE-4460 Grâce-Hollogne, Belgium • phone +32 4 296 82 00 • g-h@centexbel.be
KORTRIJK • Etienne Sabbelaan 49 • BE-8500 Kortrijk, Belgium • phone +32 56 281828 • fax +32 56 281830 • info@vkc.be
VAT BE 0459.218.289 • IBAN BE44 2100 4729 6545 • BIC GEBABEBB

Reference: T1805567 - Noss 7058 100% PES (Trevira CS), 655 g/m²

Clause 11 (upholstery composite) - Assessment of the ignitability of upholstered seating - crib ignition source no. 5

Date of ending the test 10-04-2018
 Standard used BS 5852 (2006)
 Deviation from the standard -
 Conditioning 23°C, relative humidity 50%

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test ; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Water soaking of the cover No
 Filling C55120 (Recticel) * - fire retardant foam - ± 60 kg/m³

* The filling complies with schedule 1 part 1 of the UK Furniture and Furnishings (Fire) (Safety) Regulations 1988

| | 1 | 2 |
|---|---------------------|---------------------|
| Smouldering criteria | | |
| Unsafe escalating combustion | no | no |
| Test assembly consumed | no | no |
| Smoulders to extremities | no | no |
| Smoulders through thickness | no | no |
| Smoke, heat or glowing more than 1 hour | no | no |
| Smoulders more than 100 mm from source | no | no |
| Flaming criteria | | |
| Unsafe escalating combustion | no | no |
| Test assembly consumed | no | no |
| Flames to extremities | no | no |
| Flames through thickness | no | no |
| Flame time >10 min | no | no |
| Flame time | 3 min 38 s | 5 min 28 s |
| | | |
| | non-ignition - NI/5 | non-ignition - NI/5 |

Conclusion Non-ignition - NI/5