



TESTING CERT. #3193.01

Report Number: 19-000713

Revision Number:1

Date Order Received: 02/08/2019

For the Account of: Vescom, B.V.
Sint Jozestraat 20
5753 Av Duerne

Client's Identification: Lindau 7027 test 728

CERTIFICATE OF TESTING

TEST PERFORMED: Pilling Resistance and Other Related Surface Changes of Textile Fabrics : Brush Pilling Tester ASTM D3511/D3511M-16

TEST RESULTS

Table with 2 columns: Location (Left, Center, Right, Average Rating) and Rating (3.5)

Sever fuzzing.

RATING SYSTEM

- Class 5.0 No Pilling
Class 4.0 Slight Pilling
Class 3.0 Moderate Pilling
Class 2.0 Severe Pilling
Class 1.0 Very Severe Pilling

NOTES

- Test Conditions: 70 ±4°F, 65 ±5% Relative Humidity
Sampling Method: As Received
Viewing Apparatus: Macbeth Lightbooth
Viewing Option: 45 degree
Rating Standard: ADJD3512 Photographic Standards
Running Times: 4 minutes brushing / 2 minutes pilling

ACCEPTANCE CRITERIA

- A.C.T. Standard: Acceptance Criteria
Upholstery Class 3 minimum

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Berta Stiver (Handwritten signature)

Authorized Signature

Date Order Completed: 02/16/2019