



Vescom BV
Sint Jozefstraat 20
NL-5753 AV Deurne
NEDERLAND

Your notice of
19-02-2019

Your reference

Date
02-04-2019

Analysis Report 19.01069.07

Required tests :

NF P92-507 (2004)

Identification number	Information given by the client	Date of receipt
T1904008	Long	19-02-2019



Gina Créelle
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

Reference: T1904008 - Long

Classification of materials according to their reaction to fire - Electric burner"

Date of ending the test 27-03-2019
Standard used NF P92-503 (1995)
Product standard NF P92-507 (2004)

Deviation from the standard -

Sample thickness ≤ 5 mm

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%
Minimum 7 days or until constant mass is achieved

	Length		Width	
	Face A	Face B	Face A	Face B
Hole formation	yes	yes	yes	yes
Max. afterflame time (s)	0	0	0	0
Afterglow	no	no	no	no
Afterglow with propagation in area > 25 cm	no	no	no	no
Damaged length (cm)	20.0	19.5	19.0	17.0
Damaged width (cm) in area >45 cm	0	0	0	0
Flaming molten droplets	no	no	no	no
Non-flaming molten droplets	no	no	no	no
Flaming debris	no	no	no	no
Non-flaming debris	no	no	no	no
Average damaged length (cm)	19.0			
Average damaged width (cm) in area > 45 cm	0			

Reference: T1904008 - Long

Classification of materials according to their reaction to fire - Flame persistence test"

Date of ending the test 28-03-2019
Standard used NF P92-504 (1995)
Product standard NF P92-507 (2004)

Deviation from the standard -

Sample thickness ≤ 5 mm

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%
Minimum 7 days or until constant mass is achieved

Each test has been carried out with a flame application time of 5s.

	Length		Width	
	Face A	Face B	Face A	Face B
#1	*	*	*	*
#2	*	*	*	*
#3	*	*	*	*
#4	*	*	*	*
#5	*	*	*	*
#6	*	*	*	*
#7	*	*	*	*
#8	*	*	*	*
#9	*	*	*	*
#10	*	*	*	*

Flaming debris no
Non-flaming debris yes

*: afterflame time ≤ 2 s
> 2 s: afterflame time > 2 s and ≤ 5 s
> 5 s: afterflame time > 5 s

Reference: T1904008 - Long

Classification of materials according to their reaction to fire - "Test for melting materials"

Date of ending the test 01-04-2019
Standard used NF P92-505 (1995)
Product standard NF P92-507 (2004)

Deviation from the standard -

Dimension of the specimens 70 mm x 70 mm x 2 mm

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%
Minimum 7 days or until constant mass is achieved

Four specimens, two on both sides, have been tested .

		First ignition (s)	Non-flaming debris	Flaming debris	Ignition cotton wool	Mass (g)
#1	face A	*	yes	no	no	2.2
#2	face B	*	yes	no	no	2.2
#3	face A	*	yes	no	no	2.2
#4	face B	*	yes	no	no	2.3

* no ignition

Classification M1