

CERTIFICATE OF TESTING

For the Account Of: Raxon Fabrics
2289 Ross Mill Road
Henderson, NC 27536

Contact: Barbara Crane

Client's Identification: Lamu Test #459
(Vescom B.V.; Sint Jozestraat 20; 5753 Av Duerne)

TEST PERFORMED Breaking Strength and Elongation of Textile Fabrics (Grab Test) ASTM D5034-09(2013)(G-E)

TEST RESULTS

Specimen	Breaking Force (lbf)	
1	76	
2	73	
3	73	
4	72	
5	69	
		Avg of Warp: 73
6	78	
7	77	
8	75	
9	72	
10	78	
11	77	
12	75	
13	75	
		Avg of Fill: 76


NOTES

Equipment Used: Tinius Olson H5KT Universal Testing Machine
Load Cell Maximum: 1000 pounds
Jaw Size: 1 inch x 1 inch (face and back), rubber coated
Test Conditions: 70 ±4°F, 65 ±5% Relative Humidity
Sampling Method: As Received

ACCEPTANCE CRITERIA

A.C.T. Standard	Acceptance Criteria
Upholstery	50 pounds minimum
Panels and Upholstered Walls	35 pounds minimum

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.



 Authorized Signature CR