



Vescom B.V.
Sint-Jozefstraat 20
5753 AV Deurne
NEDERLAND

Your notice of
 04-03-2019

Your reference

Date
 03-04-2019

Analysis Report 19.01316.01

Required tests :

NF P92-507 (2004)

Identification number	Information given by the client	Date of receipt
T1905070	Zanzibar	04-03-2019



Gina Créelle
 Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
 The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
 In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

Reference: T1905070 - Zanzibar

Classification of materials according to their reaction to fire - Electric burner"

Date of ending the test 02-04-2019
Standard used NF P92-503 (1995)
Product standard NF P92-507 (2004)

Deviation from the standard -

Sample thickness ≤ 5 mm

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%
Minimum 7 days or until constant mass is achieved

Only the front side has been tested

	Length		Width	
	1	2	1	2
Hole formation	no	no	no	no
Max. afterflame time (s)	6	6	6	5
Afterglow	no	no	no	no
Afterglow with propagation in area > 25 cm	no	no	no	no
Damaged length (cm)	21.5	19.5	19.0	19.5
Damaged width (cm) in area >45 cm	0	0	0	0
Flaming molten droplets	no	no	no	no
Non-flaming molten droplets	no	no	no	no
Flaming debris	no	no	no	no
Non-flaming debris	no	no	no	no
Average damaged length (cm)	20.0			
Average damaged width (cm) in area > 45 cm	0			

Classification M2