



Vescom bv
Sint-Jozefstraat 20
5753 AV Deurne
NEDERLAND

Your notice of
25-01-2019

Your reference

Date
06-03-2019

Analysis Report 19.00464.03

Required tests :

IMO - 2010 FTP Code Annex 1 - Fire Test Procedures - Test for vertically supported textiles and films
Fire test procedures - Part 7

Identification number	Information given by the client	Date of receipt
T1901856	Tay 8077	25-01-2019



Gina Créelle
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.




Reference: T1901856 - Tay 8077

IMO curtains

Information given by the client

Type of material	Curtain
Fabric	
Composition	100% polyester (Trevira CS)
Structure	Plain / weave
Number of threads - warp	62/cm
Number of threads - weft	53/cm
Yarn count - warp	Nm 450/1 CS
Yarn count - weft	Nm 70/1 CS + Nm 145/1 PES-FR + Nm 70/2 CS
Thickness in mm	0.3
Weight g/m ²	99
Colour	Beige
Inherently FR treated	yes



Reference: T1901856 - Tay 8077

Fire Test Procedures - Test for vertically supported textiles and films

Date of ending the test 05-03-2019
 Standard used IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 7
 Deviation from the standard -
 Conditioning Min 24 hours at 20°C and 65% RH

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Flame application time (s) 5 - 15
 Weight (g/m²) 101

A = front - B = back

Face A

Determination of the test conditions.

Length

	Surface		Edge	
Flame application time (s)	5	15	5	15
Afterflame time (s)	0	0	0	0
Surface flash	no	no	no	no
Edge reached	no	no	no	no
Ignition cotton wool	no	no	no	no
Maximum damaged length (mm)	31	35	41	44

No sustained ignition : testing continued under conditions showing the greatest damaged length.

Width

	Surface		Edge	
Flame application time (s)	5	15	5	15
Afterflame time (s)	0	0	0	0
Surface flash	no	no	no	no
Edge reached	no	no	no	no
Ignition cotton wool	no	no	yes	no
Maximum damaged length (mm)	33	34	56	34

No sustained ignition : testing continued under conditions showing the greatest damaged length.

Worst testing conditions

Length Edge - flame application time 15 s

	1	2	3	4	5	Average
Afterflame time (s)	0	0	0	0	0	
Surface flash	no	no	no	no	no	
Edge reached	no	no	no	no	no	
Ignition cotton wool	no	no	no	yes	no	
Maximum damaged length (mm)	44	37	30	38	50	40

Additional tests

	1	2	3	4	5	Average
Afterflame time (s)	0	0	0	0	0	
Surface flash	no	no	no	no	no	
Edge reached	no	no	no	no	no	
Ignition cotton wool	no	no	no	no	no	
Maximum damaged length (mm)	44	35	44	48	36	41

Width Edge - flame application time 5 s

	1	2	3	4	5	Average
Afterflame time (s)	0	0	0	0	0	
Surface flash	no	no	no	no	no	
Edge reached	no	no	no	no	no	
Ignition cotton wool	yes	no	no	no	no	
Maximum damaged length (mm)	56	44	49	46	34	46

Additional tests

	1	2	3	4	5	Average
Afterflame time (s)	0	0	0	0	0	
Surface flash	no	no	no	no	no	
Edge reached	no	no	no	no	no	
Ignition cotton wool	no	no	no	no	no	
Maximum damaged length (mm)	22	46	53	42	48	42

Face B

Determination of the test conditions.

Length

	Surface		Edge	
Flame application time (s)	5	15	5	15
Afterflame time (s)	0	0	0	0
Surface flash	no	no	no	no
Edge reached	no	no	no	no
Ignition cotton wool	no	no	no	no
Maximum damaged length (mm)	27	34	29	36

No sustained ignition : testing continued under conditions showing the greatest damaged length.

Width

	Surface		Edge	
Flame application time (s)	5	15	5	15
Afterflame time (s)	0	0	0	0
Surface flash	no	no	no	no
Edge reached	no	no	no	no
Ignition cotton wool	no	no	no	no
Maximum damaged length (mm)	30	37	40	43

No sustained ignition : testing continued under conditions showing the greatest damaged length.

Worst testing conditions

Length Edge - flame application time 15 s

	1	2	3	4	5	Average
Afterflame time (s)	0	0	0	0	0	
Surface flash	no	no	no	no	no	
Edge reached	no	no	no	no	no	
Ignition cotton wool	no	no	no	no	no	
Maximum damaged length (mm)	36	33	33	37	31	34

Width Edge - flame application time 15 s

	1	2	3	4	5	Average
Afterflame time (s)	0	0	0	0	0	
Surface flash	no	no	no	no	no	
Edge reached	no	no	no	no	no	
Ignition cotton wool	no	no	no	no	no	
Maximum damaged length (mm)	43	48	51	53	50	49

Criteria for curtains and drapes

1. Afterflame time ≤ 5 s for any specimen tested with face ignition.
2. No flame propagation to the edges for any specimen tested with face ignition..
3. No ignition of the cotton wool for any specimen.
4. Average char length ≤ 150 mm in any of the batches tested with face or edge ignition.
5. No occurrence of a surface flash more than 100 mm from the point of ignition.

Remark: If the test for length and/or width is carried out with edge ignition, the results obtained through the edge application are considered for the purposes of the criteria 1 and 2.

The fabric passes the proposed criteria for curtains and drapes.