

96-D Allen Boulevard Farmingdale, New York 11735-5626 USA Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956 e-mail: testing@govmark.com

					Page 2
Received:10/24/2017	Completed: 11/03	/2017 Letter: P3	RG P.O. #:	Test Report #:	3-21942-3-
Client's Style: Identification Thick		stery. Content: PVC V	inyl Upholstery. Weig	ght: 38.515 oz/lyd. Product End Use	: Upholstery.
Tested For: Damian Maldonado			Ke	y Test: ASTM D751-06 45-48/AC	CT 150
PO Box	n America (1198 son, NC 27537			Tel: 1-(252)-431-6233 Fax: 1-()	Ext:
SPECIMEN PARTICU	JLARS:				
Test Width: [x] 1" [] 2"		Face to Face Bo	onding: [] Yes [x] No	[CODE 225] [CODE 150]	
RESULTS:					
Specimen #	Machine Direction (lbf/inch)	Specimen #	Cross Machine Direction (lbf/inch)		
1	6.5	4	4.9		
2 3	10.4 7.9	5 6	5.0 5.8		
Avg	3: 8.3	Avg	g: 5.2		
REMARKS: None.					
ACCEPTANCE CRITE	ERIA: Minimum f	For Machine and C	Cross Machine Dir	ection:	
3 lbs/inch mi	inimum average				
0	OR				
Coating canno	ot be separated	d from base mater	cial (CCBS)		
CONCLUSION: Bas	sed on the repo	orted Results and	d cited Acceptanc	e Criteria, the item teste	ed:
[x] Complies;	; [] Does not	comply			
		t the above resul		l after testing specimens i	n accordance
MND		Phyllis Pett	it		
AUTHORIZED SIGNA	ATURE		NOV 0 9 2017		
/pm/AC		(Paç	ge 2 of 2)		