



Received: 10/24/2017 | Completed: 11/03/2017 | Letter: P3 | RG | P.O.#: | Test Report #: 3-21942-3-

Client's Identification | Style: PVC Vinyl Upholstery. Content: PVC Vinyl Upholstery. Weight: 38.515 oz/lyd. Product End Use: Upholstery.
Thickness: 0.0460in.

Tested For: **Damian Maldonado** | Key Test: ASTM D751-06 45-48/ACT 150
Vescom America | Tel: 1-(252)-431-6233 | Ext:
PO Box 1198 | Fax: 1-()- -
Henderson, NC 27537

SPECIMEN PARTICULARS:

Test Width: 1" | Face to Face Bonding: Yes [CODE 225]
 2" | No [CODE 150]

RESULTS:

Specimen #	Machine Direction (lbf/inch)	Specimen #	Cross Machine Direction (lbf/inch)
1	6.5	4	4.9
2	10.4	5	5.0
3	7.9	6	5.8
Avg: 8.3		Avg: 5.2	

REMARKS: None.

ACCEPTANCE CRITERIA: Minimum for Machine and Cross Machine Direction:

3 lbs/inch minimum average

-- OR --

Coating cannot be separated from base material (CCBS)

CONCLUSION: Based on the reported Results and cited Acceptance Criteria, the item tested:

Complies; Does not comply

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment cited above.

AUTHORIZED SIGNATURE
GOVMARK
/pm/AC

Phyllis Pettit

NOV 09 2017

(Page 2 of 2)