



Received: 10/24/2017 Completed: 11/06/2017 Letter: P4 RV P.O.#: Test Report #: 3-21942-4-

Client's Identification Style: PVC Vinyl Upholstery. Content: PVC Vinyl Upholstery. Weight: 38.515 oz/lyd. Product End Use: Upholstery. Thickness: 0.0460in.

Tested For: **Damian Maldonado** Key Test: ASTM D 2261/ACT 150  
 Vescom America  
 PO Box 1198 Tel: 1-(252)-431-6233 Ext:  
 Henderson, NC 27537 Fax: 1-( )- -

Test Category: Tongue Tear Coated Fabrics Specifier: ACT LE 2015: V 8/15  
 PC: 15H NTR 9/15 dl/SM

TEST PERFORMED: ASTM D 2261-02 - Standard Test method for Tearing Strength of Fabrics by the Tongue (Single Rip) Procedure [CRE Machine] --

As cited by the ACT Voluntary Performance Guidelines (January 2015)

PRODUCT CATEGORY: Upholstery - Coated Fabrics, Knits and Wovens

BASE MATERIAL:  Knit;  Woven

RESULTS:	Against Machine Direction	Against Cross Machine Direction
Specimen #	(lbs)	(lbs)
1	7.4	9.9
2	6.4	8.2
3	8.3	8.9
4	6.0	9.3
5	8.5	9.8
Avg:	7.3	9.2

REMARKS: None.


ACCEPTANCE CRITERIA:

Machine Direction: 4 lbs. minimum average  
 Cross Machine Direction: 4 lbs. minimum average

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

Complies;  Does not comply

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

  
 AUTHORIZED SIGNATURE  
 GOVMARK  
 /pm/AC

Phyllis Pettit

NOV 09 2017