

dikson

7063.01 - 7063.14



binder

upholstery 02

descripción

**tapicería de mezcla sofisticada de hilos
suaves de chenilla**

composición

100% poliéster ignífugo

ancho

± 140 cm, ± 55 inches

peso

± 819 gr/m¹, ± 26 oz/yd¹ fabrics

combustión retardada

EN 1021/ 1-2

BS 5852, crib 5

NF P 92 / 503 - 507, M1

DIN 4102, B1

UNI 9175, classe 1.IM

Cal TB 117

NFPA 260, class 1

IMO 2010 FTP part 8

resistencia al desgaste

ISO 12947-2

100.000 rubs martindale

ASTM D4157

100.000 double rubs wyzenbeek

pilling

ISO 12945-2

4-5 (escala 1-5)

ASTM D3511

5 (escala 1-5)

resistencia al frotamiento

ISO 105-X12

mojado 4-5 / seco 4-5 (escala 1-5)

AATCC 8

mojado 4 / seco 4 (escala 1-5)

insensibilidad a la luz

ISO 105-B02

6 (escala 1-8)

AATCC 16.3: 40 hours

4.5 (escala 1-5)

resistencia al deslizamiento de costuras

ISO 13936 - 2

lizo 2 mm / trama 2 mm

ASTM D4034

lizo 89 lbs / trama 96 lbs

resistencia a la tensión

ISO 13934-1

warp 2500 N / weft 1550 N

ASTM D5034

warp 474 lbs / weft 262 lbs

mantenimiento




carencia: lizo -2% / trama -1.8%



**CONFIDENCE
IN TEXTILES**
Tested for harmful substances
according to Oeko-Tex® Standard 100

dikson


7063.01 - 7063.14



7063.01




7063.02



7063.03




7063.04



7063.05



7063.06



7063.07



7063.08



7063.09




7063.10



7063.11



7063.12



7063.13



7063.14