

acton

7062.01 - 7062.39



binder

upholstery

omschrijving

sterke meubelstof in melange optiek, in breed kleurengamma

samenstelling

87% recycled polyester FR / 13% polyester FR

breedte

± 141 cm, ± 56 inches

gewicht

± 605 gr/m¹, ± 20 oz/yd¹ fabrics

brandwerendheid

EN 1021/ 1-2

BS 5852, crib 5

NF P 92 / 503 - 507, M1

DIN 4102, B1

UNI 9175, classe 1.IM

Cal TB 117

NFPA 260, class 1

IMO 2010 FTP part 8

slijtvastheid

ISO 12947-2

90.000 rubs martindale

ASTM D4157

100.000 double rubs wyzenbeek

pilling

ISO 12945-2

4 (schaal 1-5)

ASTM D3511

5 (schaal 1-5)

wrijftechtheid

ISO 105-X12

nat 4-5 / droog 4-5 (schaal 1-5)

AATCC 8

nat 5 / droog 5 (schaal 1-5)

lichtechtheid

ISO 105-B02

6 (schaal 1-8)

AATCC 16.3: 40 hours

4 (schaal 1-5)

naadschuifweerstand

ISO 13936 - 2

ketting 3.7 mm / inslag 3.7 mm

ASTM D4034

ketting 109 lbs / inslag 86 lbs

treksterkte

ISO 13934-1

warp 1380 N / weft 1790 N

ASTM D5034

warp 263 lbs / weft 345 lbs

onderhoud



krimp: ketting -2.7% / inslag -0.6%



































STANDARD
100

S07-0023
Hohenstein HTTI

acton

7062.01 - 7062.39

								
7062.01	7062.02	7062.03	7062.04	7062.05	7062.06	7062.07	7062.08	7062.09
								
7062.10	7062.11	7062.12	7062.13	7062.14	7062.15	7062.16	7062.17	7062.18
								
7062.19	7062.20	7062.21	7062.22	7062.23	7062.24	7062.25	7062.26	7062.27
								
7062.28	7062.29	7062.30	7062.31	7062.32	7062.33	7062.34	7062.35	7062.36
								
7062.37	7062.38	7062.39						