


jemo

7044.01 - 7044.21



binder

upholstery

vinyl

description

appearance and structure similar to that of fine woven textile

composition

vinyl coat, cotton/polyester backing

width

± 54-55 inches, ± 137-140 cm

weight

backing: ± 110 gr/m², ± 5 oz/yd¹

coating: ± 690 gr/m², ± 31 oz/yd¹

thickness

1.1 mm, 0.04 inches

flame retardancy

EN 1021/1-2

BS 5852, crib 5

NF P 92/503 – 507, M2

NF D60-013 (AM 18)

DIN 4102, B2

UNI 9175, classe 1 IM

Cal TB 117

NFPA 260, class 1

IMO 2010 FTP part 8

abrasion

ISO 12947-2

> 300.000 rubs martindale

ASTM D4157

100.000 double rubs wyzenbeek

colorfastness to crocking

ISO 105-X12

wet 5 / dry 5 (scale 1-5)

AATCC 8

wet 5 / dry 5 (scale 1-5)

colorfastness to light

ISO 105-B02

7 (scale 1-8)

ASTM D4329: 150 hours

4 (scale 1-5)

resistance to blood, urine, sweat and sebum

EN 12720

5 (scale 1-5)

breaking strength

ISO 1421

length 475 N / width 313 N

ASTM D2261

length 7.3 lbs / width 9.2 lbs

flexibility

ISO 7854

400.000 cycles

adhesion to coating


ASTM D751

length 8.3 lbf / width 5.2 lbf




jemo


7044.01 - 7044.21




7044.01




7044.02




7044.03




7044.04




7044.05




7044.06




7044.07




7044.08



7044.09




7044.10




7044.11




7044.12




7044.13




7044.14



7044.15




7044.16




7044.17




7044.18



7044.19



7044.20



7044.21