

lani

7060.01 - 7060.56



binder

upholstery

description

tough, felted wool quality in modern applicable colours

composition

80% wool / 20% polyamide

width

± 55 inches, ± 140 cm

weight

± 21 oz/yd¹, ± 640 gr/m¹ fabrics

flame retardancy

EN 1021/ 1-2

BS 5852, crib 5 with FR finish

DIN 4102, B2 with FR finish

UNI VF 9175, classe 1 IM

Cal TB 117

NFPA 260, class 1

IMO 2010 FTP part 8

NF D 60-013 - AM18

abrasion

ISO 12947-2

>300.000 rubs martindale

ASTM D4157

100.000 double rubs wyzenbeek

pilling

ISO 12945-2

4 (scale 1-5)

ASTM D3511

2.5 (scale 1-5)

colorfastness to crocking

ISO 105-X12

wet 4 - 5 / dry 4 - 5 (scale 1-5)

AATCC 8

wet 5 / dry 5 (scale 1-5)

colorfastness to light

ISO 105-B02

5-7 (scale 1-8)

AATCC 16.3: 40 hours

3.5 (scale 1-5)

seam slippage

ISO 13936 - 2

warp 2.6 mm / weft 3 mm

ASTM D4034

warp 125 lbs / weft 116 lbs

breaking strength

ASTM D5034

warp 206 lbs / weft 202 lbs

care





STANDARD
100

S10-0100
Hohenstein HTTI

lani

7060.01 - 7060.56




7060.01



7060.02



7060.03



7060.04



7060.05




7060.06



7060.07



7060.08



7060.09



7060.10



7060.11



7060.12



7060.13



7060.14



7060.15




7060.16




7060.17




7060.18




7060.19




7060.20



7060.21



7060.22



7060.23




7060.24




7060.25



7060.26



7060.27



7060.28



7060.29



7060.30




7060.31



7060.32



7060.33



7060.34



7060.35




7060.36



7060.37



7060.38




7060.39



7060.40




7060.41




7060.42




7060.43




7060.44



7060.45



7060.46




7060.47




7060.48



7060.49




7060.50



7060.51




7060.52




7060.53



7060.54



7060.55



7060.56