

zanzibar

7059.01 - 7059.34



binder

upholstery

description

uni mohair, standing pile in rich colours

composition

100% mohair (base: cotton)

width

± 55 inches, ± 140 cm

weight

± 26 oz/yd¹, ± 805 gr/m¹ fabrics

flame retardancy

EN 1021/ 1-2

BS 5852, crib 5

NF P 92 / 503 – 507, M2 with FR finish

DIN 4102, B2

UNI 9175, classe 1 IM

Cal TB 117

NFPA 260, class 1

IMO 2010 FTP part 8

abrasion

ASTM D4157

100.000 double rubs wyzenbeek

pilling

ISO 12945-2

4 – 5 (scale 1–5)

ASTM D3511

5 (scale 1–5)

colorfastness to crocking

ISO 105-X12

wet 4 – 5 / dry 4 – 5 (scale 1–5)

AATCC 8

wet 4.5 / dry 5 (scale 1–5)

colorfastness to light

ISO 105-B02

5 (scale 1–8)

AATCC 16.3: 40 hours

3 (scale 1–5)

seam slippage

ISO 13936 – 2

warp 2 mm / weft 2.5 mm

ASTM D4034

warp 79 lbs / weft 82 lbs

breaking strength

ASTM D5034

warp 136 lbs / weft 107 lbs

additional information

cradle to cradle bronze certified

care



dry clean only


















STANDARD
100
1207035
Centexbel



zanzibar

7059.01 - 7059.34

								
7059.01	7059.02	7059.03	7059.04	7059.05	7059.06	7059.07	7059.08	7059.09
								
7059.10	7059.11	7059.12	7059.13	7059.14	7059.15	7059.16	7059.17	7059.18
								
7059.19	7059.20	7059.21	7059.22	7059.23	7059.24	7059.25	7059.26	7059.27
								
7059.28	7059.29	7059.30	7059.31	7059.32	7059.33	7059.34		