




binder

upholstery

描述

可用于两侧的双色羊毛家具面料

组成

80%羊毛 / 20%聚酰胺

宽度

± 140 cm, ± 55 inches

重量

± 536 gr/m¹, ± 17 oz/yd¹ fabrics

阻燃

EN 1021/1-2

BS 5852, crib 5

UNI 9175, classe 1 IM

Cal TB 117

NFPA 260, class 1

IMO 2010 FTP part 8

NF D 60-013 - AM18

耐磨性

ISO 12947—2

100,000 rubs martindale

ASTM D4157

45,000 double rubs wyzenbeek

起毛

ISO 12945-2

3 (由 1—5)

ASTM D3511

2,5 (由 1—5)

耐擦拭

ISO 105—X12

湿 4 / 干 4-5 (由 1—5)

AATCC 8

湿 5 / 干 4.5 (由 1—5)

耐褪色

ISO 105—B02

浅 4-5 / 深 4-5 (由 1—8)

AATCC 16,3: 40 hours

5 (由 1—5)

耐滑缝

ISO 13936 — 2

纵向收缩比 4 mm / 横向收缩比 3,5 mm

ASTM D4034

纵向收缩比 39 lbs / 横向收缩比 89 lbs

屈伸强度

ASTM D5034

warp 186 lbs / weft 224 lbs























STANDARD
100

S10-0100
Hohenstein HTTI

lindau

7028.01 - 7028.33

								
7028.01	7028.15	7028.13	7028.04	7028.09	7028.22	7028.19	7028.20	7028.26
								
7028.02	7028.14	7028.10	7028.08	7028.18	7028.21	7028.23	7028.32	7028.30
								
7028.03	7028.12	7028.07	7028.11	7028.31	7028.28	7028.24	7028.29	7028.33
								
7028.06	7028.05	7028.16	7028.17	7028.27	7028.25			