

burton

7056.01 - 7056.23



binder

upholstery

描述

双色混编素色面料

组成

100%特弗拉阻燃纤维

宽度

± 140 cm, ± 55 inches

重量

± 763 gr/m¹, ± 25 oz/yd¹ fabrics

阻燃

EN 1021/ 1—2

BS 5852, crib 5

NF P 92 / 503 — 507, M1

DIN 4102, B1

UNI 9175, classe 1 IM

Cal TB 117

NFPA 260, class 1

IMO 2010 FTP part 8

耐磨性

ISO 12947—2

80,000 rubs martindale

ASTM D4157

100,000 double rubs wyzenbeek

起毛

ISO 12945—2

4 (由 1—5)

ASTM D3511

4 (由 1—5)

耐擦拭

ISO 105—X12

湿 4 — 5 / 干 4 — 5 (由 1—5)

AATCC 8

湿 5 / 干 5 (由 1—5)

耐褪色

ISO 105—B02

6 — 7 (由 1—8)

AATCC 16,3: 40 hours

4.5 (由 1—5)

耐滑缝

ISO 13936 — 2

纵向收缩比 3 mm / 横向收缩比 2.7 mm

ASTM D4034

纵向收缩比 101 lbs / 横向收缩比 107 lbs

屈伸强度

ASTM D5034

warp 365 lbs / weft 289 lbs



收缩□：纵向收缩比 -0.7% / 横向收缩比 -0.6%



收缩□：纵向收缩比 -1.8% / 横向收缩比 -2.2%



STANDARD
100


S07-0023
Hohenstein HTTI

burton


7056.01 - 7056.23




7056.01




7056.02




7056.03




7056.04




7056.05




7056.06




7056.07



7056.08




7056.09




7056.10



7056.11




7056.12




7056.13




7056.14




7056.15




7056.16



7056.17




7056.18



7056.19




7056.20



7056.21



7056.22



7056.23